

SPECIFICATION OF BITUMEN 60/70



Introduction

BS group Bitumen Grade 60/70 is a standard penetration grade Bitumen usually used as a paving Bitumen suitable for road construction and other industrial purposes. This grade of Bitumen is mainly used for hot mix especially in moderate climate.

Typical properties

Description	Unit	Limit	Test Method
Density@25°C	Kg/m ³	1010-1060	ASTM D70 or D3289
Penetration@25°C	mm/10	60-70	ASTM D5
Softening Point	°C	49-56	ASTM D36
Ductility@25°C	cm	100min	ASTM D113
Loss on Heating	wt%	0.2max	ASTM D6
Drop in Penetration after Heating	%	20max	ASTM D5
Flash Point	°C	232min	ASTM D92
Solubility in Trichloroethylene	wt%	99.0min	ASTM D2042
Spot Test	---	Negative	A.A.S.H.O.T.102
Viscosity@60°C	P	2000±400	ASTM D2171
Viscosity@135°C	cSt	300min	ASTM D2170

Applications

This kind of bitumen is suitable to be used for road construction projects in mild regions. Also it can be used for producing some kind of asphalt primer and Waterproofing products.

Hazard Identification

NOT classified as dangerous in accordance with Directive 67/548/EEC or EC 1272/2008.

The main hazards presented by Asphalt relate to the temperature of the material. The following hazards may apply:

- Hot materials may burn the skin.
- Fumes from Asphalt are unlikely to be hazardous when laid in open air situations, but there may be a risk to health by continuous inhalation of high vapor concentrations which might arise in poorly ventilated, confined or semi-confined spaces.

- Asphalt is not a dusty material, but respirable dust may be released by cutting, drilling or planing hardened asphalt. If inhaled in excessive quantities over a prolonged period or extended period, respirable dust can constitute a long term health hazard.

Dusts containing Respirable Crystalline Silica* (quartz) present a greater hazard. Long-term exposure to respirable dust can lead to respiratory system damage and disease. Respirable crystalline silica* has been associated with the lung disease silicosis.

The quartz content of the product will vary, and is related to the type of aggregate used in the production of the asphalt. Advice on the quartz content and other chemical information is available from the supplying unit.

Fire Fighting Measures

Suitable Extinguishing Media: Dry powder, foam.

Unsuitable Extinguishing Media: Do not use water. CO2 is also not suitable.

Special Exposure Hazards in Fire: Hydrocarbon fumes may be released, along with other hazardous combustion products including smoke.

Special Protective Equipment for Fire Fighters: Proper protective equipment including suitable respirators or breathing apparatus must be worn.

Handling and Storage

Handling:

Skin contact with the product should be avoided. Inhalation of fumes should be avoided as far as is reasonably practicable.

If the formation of vapors is a risk, then additional ventilation should be provided. Handle away from sources of ignition and heat. Do not smoke, eat or drink during use.

Storage:

No special requirements. Asphalt is normally used upon receipt.

Refer to the relevant Technical Data Sheet for the specific product.

Cleaning

Tools: Clean with kerosene and gasoline.

Hands: Use a hand cleanser or kerosene followed by soap and water.

Availability

BS group Bitumen Penetration Grade 60/70 is available in:

- Bulk
- New Steel Drums (185 Kg) and (150 Kg)